



ApliTape™ is the **original** RTape application tape in an affordably priced, factory cut, razor slit roll.

ApliTape

Works in either **wet or dry applications**, with no adhesive transfer

Available in standard and heavyweight paper grads, in a **variety of tack levels**

No adhesive build-up on stored graphics

No adhesive balls, gapping between layers or crushed edges

Removes easily following graphics application

If adhesive touches adhesive, it pulls apart easily with no adhesive delamination

Medium Tack 4050

- Standard grade saturated paper application tape
- Medium tack rubber adhesive

High Tack 4075

- Standard grade saturated paper application tape
- High tack rubber adhesive

Ultra high Tack 4885

- Premium grade screen print application tape
- Ultra tack rubber adhesive

Applications

General Purpose Sign Applications

Screen Printing

Digital Printing



TECHNICAL DATA ▶

		4050	4075	4885
Physical Properties				
Adhesive	Rubber-based			
Colour	White/Translucent			
Tensile	297 N/100 mm			
Elongation	3-4%			
Tear Resistance	50 grams			
Thickness	Tape	100-113 μ	100-113 μ	127-140 μ
	Tape + Adhesive	125-138 μ	125-138 μ	152 μ
Tack Level		Medium	High	Ultra high
Adhesion*	Steel	13-15 N/100mm	18-20 N/100mm	>22 N/100mm

* Adhesion PSTC-1, 1 minute on stainless steel at time of manufacture, 2 minute dwell on stainless steel

Conditions for Use	
Shelf Life**	1 year

** Stored at 22°C /50-55% RH

STOCKED PRODUCTS ▶

	Tack Level	Size	SKU #	Rolls/Case	Rolls/Pallet
4050	Medium	1000mm x 100m	1416050	1	49
		1220mm x 100m	1416090	1	49
4075	High	1000mm x 100m	1478552	1	49
		1220mm x 100m	1478772	1	49
4885	Ultra high	1000mm x 100m	1490764	1	36
		1220mm x 100m	1490775	1	36



WARRANTY Tapes are only warranted to be free of defects in workmanship or materials at time of shipment. Nekoosa will replace or credit any material deemed to be defective. No acceptance or responsibility for loss, damage, or expense, implied or otherwise, shall be assumed by the seller or manufacturer. The end user assumes all risk and liability.

The information provided herein is correct to the best of Nekoosa's knowledge. No liability for any errors, facts or opinions are accepted. Customers must satisfy themselves as to the suitability of this product for their application. No responsibility for any loss as a result of any person placing reliance on any material contained herein will be accepted.